

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
4 April 2002 (04.04.2002)

PCT

(10) International Publication Number
WO 02/26701 A2

- (51) International Patent Classification⁷: C07C 275/02
- (21) International Application Number: PCT/GB01/04300
- (22) International Filing Date:
26 September 2001 (26.09.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
0023706.5 27 September 2000 (27.09.2000) GB
- (71) Applicant (for all designated States except US): SCIONIX LIMITED [GB/GB]; Marlborough House, 298 Regents Park Road, Finchley, London N3 2UA (GB).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): ABBOTT, Andrew, Peter [GB/GB]; 16 Shirley Avenue, Leicester LE2 3NA (GB). DAVIES, David, Lloyd [GB/GB]; 5 Mosse Way, Oadby, Leicester LE2 4HL (GB). CAPPER, Glen [GB/GB]; 45 Scott Drive, Exmouth, Devon EX8 4NH (GB). RASHEED, Raymond, Kelvin [GB/GB]; Pennine View, Faugh, Brampton, Cumbria CA4 9EG (GB). TAM-BYRAJAH, Vasuki [LK/LK]; 51 Yasodhara Mawatha, Sri Saranankara Road, Dehiwala (LK).
- (74) Agent: RAYNOR, John; W. H. Beck, Greener & Co., 7 Stone Buildings, Lincoln's Inn, London WC2A 3SZ (GB).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:
— without international search report and to be republished upon receipt of that report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

WO 02/26701 A2

(54) Title: IONIC LIQUIDS AND THEIR USE AS SOLVENTS

(57) Abstract: Ionic compounds with a freezing point of up to 100 °C are formed by the reaction of an one amine salt of formula (I) R¹ R² R³ R⁴ N⁺ X⁻, such as choline chloride with an organic compound (II) capable of forming a hydrogen bond with X⁻, such as urea, wherein the molar ratio of I to II is from 1:1.5 to 1:2.5. R¹, R², R³ and R⁴ may be H, optionally substituted C₁ to C₃ alkyl, optionally substituted C₆ to C₁₀ cycloalkyl, optionally substituted C₆ to C₁₂ aryl, optionally substituted C₇ to C₁₂ alkaryl, or R¹ and R² taken together may represent a C₄ to C₁₀ optionally substituted alkylene group, thereby forming with the N atom of formula I a 5 to 11-membered heterocyclic ring and all of R¹, R², R³ and R⁴ are not identical, X⁻ may be NO₃⁻, F⁻, Cl⁻, Br⁻, I⁻, BF₄⁻, ClO₄⁻, CN⁻, SO₃CF₃⁻, or COOCF₃⁻. The ionic compounds are useful as solvents, and electrolytes for example in electroplating, electrowinning, and electropolishing, and as catalysts.

Ionic Liquids and Their Use as Solvents

This invention relates to ionic compounds and methods for their preparation. In particular the invention relates to ionic compounds which are liquid at relatively low temperatures, i.e. generally below about 100°C, and preferably below about 60°C and
5 more preferably which are liquid at or near to ambient temperature.

There is much current interest in the field of ionic liquids. Such systems, which are examples of molten salts, have a number of interesting and useful chemical properties, and have utility, for example, as highly polar solvents for use in preparative chemistry, and as catalysts. They also have particular application in electrochemistry, for example
10 in batteries, fuel cells, photovoltaic devices and electrodeposition processes, for example in baths for the electroplating of metals.

Generally speaking, ionic liquids have very low vapour pressure and thus, in contrast to many conventional solvents, are very advantageous in that they produce virtually no hazardous vapours. They are therefore advantageous from a health, safety and
15 environmental point of view.

One such system which has been known for many years is that formed from 1-ethyl-3-methylimidazolium chloride-aluminium chloride (EMIC-AlCl₃). This system is a thermally stable liquid between -100°C to ca. 200°C, dependent on the molar ratio of EMIC to AlCl₃ utilised.

20 Such EMIC-AlCl₃ systems have been used extensively as solvents for various ionic reactions and as electrolytes, as described, for example in US-A-5525567, FR-A-2611700, FR-A-2626572, WO95/21872, and EP-A-838447. There are a number of difficulties in utilising such compounds. These arise principally from their cost, and from their water sensitivity.

25 In recent years, other ionic compounds have been made which are liquid at relatively low temperatures. For example, US-A-4764440 discloses low temperature molten compositions, formed by reacting, for example, trimethylphenylammonium chloride with aluminium trichloride. The resulting ionic compound has a low freezing point (around -75°C), but suffers from the same water sensitivity as EMIC-AlCl₃, because of

the presence of aluminium trichloride.

Proposals have been made to utilise other metal halides, in place of aluminium trichloride. For example, US-A-5731101 discloses the use of iron and zinc halides as the anion portion of an ionic liquid composition. The cation portion is formed by an amine hydrohalide salt, of the formula $R_3N.HX$ ($X = \text{halide}$). This reference indicates however that the aluminium compounds are preferred.

PCT/GB00/01090 discloses ionic liquids, formed by the reaction of quaternary ammonium compounds such as choline chloride with halides of zinc, tin, or iron.

SAITO, SHUJI ET AL: "Complexes of urea and symmetrical tetraalkylammonium halides" J. AM. CHEM. SOC. (1966), 88(22), 5107-12 discloses complexes of urea and symmetrical Tetraalkylammonium halides. The complexes are crystalline, and there is no disclosure of the use of asymmetrical ammonium compounds, nor of the use of liquids formed from such complexes as solvents.

KOICHI TANAKA ET AL: "Molecular aggregation of alkyltrimethylammonium bromide and alcohol in the solid state" MOL. CRYST. LIQ. CRYST., Vol. 277, 1996, pages 139-143 is concerned with the separation of primary alcohols from mixtures of primary and secondary alcohols, by complexation with quaternary ammonium bromides with an alkyl chain length of at least 10.

O. KRISTIANSOON ET AL: "Interaction between methanol and $C1^-$, Br^- , I^- , $N03^-$, $C104^-$, $S03CF3^-$ and $PF6^-$ Anions studied by FTIR spectroscopy" ACTA CHEMICA SCANDINAVICA, vol. 51, 1997, pages 270-273 discloses compounds formed between quaternary ammonium cations and methanol

KELJU SAWADA ET AL: "X-Ray analyses of complexes formed between surfactants and aromatic compounds. I. A common structural pattern of complexes" BULLETIN OF THE CHEMICAL SOCIETY OF JAPAN., Vol. 71, 1998, pages 2109-2118 discloses the production of various solid materials from quaternary amines and a variety of aromatic compounds

NEGITA ET AL: " ^{14}N Nuclear quadrupole resonance of the molecular complexes of

urea" BULLETIN OF THE CHEMICAL SOCIETY OF JAPAN., Vol. 54, 1981, pages 391-393 discloses solid complexes of urea with quaternary amines.

MASOOD A. KAHN: "Hydrogen bonding and crystal packing trends in tetra-alkylammonium halide-catechol complexes: Synthesis, spectroscopic and crystal structure studies of Me₄NCl-catechol, Et₄NCl-catechol, Et₄NBr-catechol and Pr₄NBr-catechol complexes."

JOURNAL OF MOLECULAR STRUCTURE, Vol. 145, 1986, pages 203-218 discloses crystalline compounds prepared from symmetrical amines and catechol


US 5 731 101 A (LACROIX CHRISTINE P M ET AL) 24 March 1998 (1998-03-04) and MASOOD A. KAHN ET AL: "novel hydrogen bonding in crystalline tetra-n-butylammonium salts of catechol halides" CANADIAN JOURNAL OF CHEMISTRY, Vol. 63, 1985, pages 2119-2122 disclose low temperature ionic liquid compositions prepared from aluminium trichloride and triethylamine

Q. LI; T.C.W. MAK: "Novel inclusion compounds consolidated by host-host and by host-guest hydrogen bonding: complexes of thiourea with (2-hydroxyethyl)trimethylammonium carbonate and oxalate" discloses solid inclusion compounds prepared from thiourea and quaternary ammonium compounds.

We have now found that it is possible to form compounds which are liquid at temperatures of 100°C or below by reacting an amine salt, preferably a quaternary amine salt, with an organic material, preferably one which is a solid at 20°C, and which is capable of forming a hydrogen bond with the anion of the amine salt. Compounds suitable for forming such hydrogen bonds include amides, such as urea, thiourea, and acetamide, carboxylic acids such as oxalic acid, benzoic acid and citric acid, alcohols, phenol, and substituted phenols, as well as sugars such as fructose. Although it is not intended to be bound by any particular theory of operation, it is believed that hydrogen bonding of the organic compound with the anion of the ammonium compound allows charge delocalisation, which stabilises the liquid form of the compound.

According to the invention, there is provided an ionic compound, having a freezing point of up to 100°C preferably up to 60°C, formed by the reaction of at least one

amine salt of the formula



- 5 with at least one organic compound (II) which is preferably a solid at 20°C, and which is capable of forming a hydrogen bond with X⁻,
 wherein R¹ R² R³ and R⁴ are each independently:-
 H,
 optionally substituted C₁ to C₅ alkyl,
 10 optionally substituted C₆ to C₁₀ cycloalkyl,
 optionally substituted C₆ to C₁₂ aryl
 optionally substituted C₇ to C₁₂ alkaryl, or wherein
 R¹ and R² taken together represent a C₄ to C₁₀ optionally substituted alkylene group,
 thereby forming with the N atom of formula I a 5 to 11-membered heterocyclic ring,
 15 X is NO₃⁻, F, Cl⁻, Br⁻, I, BF₄⁻, ClO₄⁻, CN⁻, SO₃CF₃⁻, or COOCF₃⁻, and wherein the term
 "optionally substituted" means that the group in question may or may not be substituted
 with at one or more groups (preferably from 0 to 6 groups) selected from OH, SH, SR⁵,
 Cl, Br, F, I, NH₂, CN, NO₂, COOR⁵, CHO, COR⁵ and OR⁵, wherein R⁵ is a C₁ to C₁₀
 alkyl or cycloalkyl group, and wherein the molar ratio of I to II is from 1:1.5 to 1:2.5.
- 20 Compound II is preferably a compound of the formula R⁶COOH, R⁷R⁸NH, R⁹CZNH₂,
 or R¹⁰OH, wherein:-
 R⁶, R⁷, R⁸, R¹⁰ are each H, a C₁-C₈ alkyl group, an aryl group, or a C₇-C₁₂ alkaryl
 group optionally substituted with from 0 to 6 groups selected from OH, SR⁵, Cl, Br, F,
 I, NH₂, CN, NO₂, COOR⁵, COR⁵ and OR⁵, wherein R⁵ is H, a C₁ to C₁₀ alkyl or
 25 cycloalkyl group
 R⁹ is a group as defined for R⁶, or NHR¹¹, wherein R¹¹ is H or a C₁-C₆ alkyl group, and
 Z is O or S.
- Preferably, Compound II is urea, aniline, or a substituted aniline, a C₁-C₆ aliphatic acid,
 a C₁-C₆ aliphatic amine, a C₁-C₆ hydroxy aliphatic acid, or a dicarboxylic acid of the
 30 formula HOOC(CH₂)_nCOOH, wherein n is 0 or 1 acetamide, a phenol or a substituted
 phenol, an alkylene glycol, or citric acid. Most preferably, compound II is urea,

acetamide, oxalic acid dihydrate, phenol, ethylene glycol, or citric acid.

The Compounds I and II are mixed in a molar ratio of from 1:1.5 to 1:2.5, preferably about 1:2. In general, the amine salts (I) used in the preparation of the ionic compounds according to the invention are preferably asymmetric, i.e., the substituent groups (R^1 , R^2 , R^3 and R^4) are preferably not all identical.

The preferred amine salts of Formula I are the same as those which are preferred in PCT/GB00/01090, namely ones where R^4 is a C_1 to C_{10} alkyl or a cycloalkyl group, substituted with at least one group selected from OH, Cl, Br, F, I, NH_3 , CN, NO_2 , OR^5 , $COOR^5$, CHO, and COR^5 . It is particularly preferred that R^4 is an ethyl group, substituted with one or more of hydroxyl, chlorine, or an ester (i.e. that the substituent R^4 is derived from choline, chlorocholine, or a chlorocholine ester). Specific examples of R^4 groups which have been found to be suitable are 2-hydroxyethyl, 2-bromoethyl, 2-chloroethyl, 2-acetoethyl, N-decyl, cyclohexyl, 2-hydroxy 3-chloropropyl, and 3-bromopropyl. In a further preferred embodiment, the amine cation is chiral.

The counter-ion X^- of compound (I) is preferably halide, for example bromide or chloride.

The ionic compounds according to the invention may be prepared simply by mixing the amine salt (I), with the hydrogen bond donor (II). The reaction is generally endothermic, and is usually carried out by heating, for example to a temperature of 100°C or more.

The ionic compounds according to the invention may be utilised for a wide range of purposes, for example as electrolytes in electrochemical devices such as batteries or fuel cells, in photovoltaic or electrochromic devices, and in electrochemical deposition electropolishing, or electro-refining. The compounds find particular application for carrying out applications where a polar but non-aqueous solvent is required. They may also be employed as inert media, for dissolving ionic species such as transition metal complexes, and, either alone, or after complexing with other metal ions, as catalysts, or as chemical reagents. They may also be used for extracting a solute from an immiscible solvent.

The ionic compounds according to the invention also may be used as an alternative to the traditional mixtures of strong acids as solvents for the electropolishing of metals, for example stainless steel and aluminium. At least the preferred compounds according to the invention are more environmentally friendly than the traditional acid mixtures used for electropolishing stainless steel, as well as being cheap and reusable. In addition they can result in lower power consumption and reduced local environmental hazards in the workplace, for example those caused by gas evolution such as 'misting' of conventional acid mixtures.

A number of preferred embodiments of the invention are illustrated in the following examples. The composition of all of the products was characterised using ^1H NMR spectroscopy, and their ionic character was characterised by conductivity measurements, using a Jenway 4071 conductivity meter and temperature probe. All of the compounds had an electrical conductivity of at least $10\ \mu\text{S cm}^{-1}$ at 10°C above their freezing point. The starting materials used in the Examples were all anhydrous materials, and were dried under vacuum for 2 hours prior to use.

Example 1

Choline chloride (a quaternary ammonium compound of the general formula I above, in which R^1 , R^2 , and R^3 are methyl, R^4 is $\text{C}_2\text{H}_4\text{OH}$, and X^- is Cl^-) 1.40g (0.01 mol) was added to 1.2g of urea (0.02 mol) in a laboratory test tube. The mixture was heated to a temperature of 70°C for a period of 20 min, to produce a clear colourless liquid. The melt was allowed to cool at a rate of approximately 1°C per minute, and the temperature recorded at which initial crystal formation was observed and recorded as the freezing point. (For all eutectic mixtures, complete freezing of the composition takes place at a temperature much lower than that of initial crystal formation, but the solidification is slow, and in some cases the materials can remain as gels for several days before solidification). The conductivity of the 2:1 Urea/choline chloride ionic liquid at 19°C was $338\ \mu\text{S cm}^{-1}$. The freezing point of the mixture was 12°C .

The procedure of Example 1 was repeated, using 0.02 mols of the compounds "II" identified in Table 1, in place of urea. The results are shown in Table 1. In each case, the heating was carried out until a clear melt was formed, and the freezing point was then determined by the first appearance of crystal formation, at a cooling rate of 1°C
5 per minute.

<u>Table 1</u>		
<u>Example No</u>	<u>Compound II</u>	<u>Fr Pt. of Melt (°C)</u>
	<u>Amides</u>	
1	Urea, NH_2CONH_2	12
2	Acetamide, CH_3CONH_2	51
3	Thiourea, NH_2CSNH_2	69
4	Salicylamide, $o\text{-HOC}_6\text{H}_4\text{CONH}_2$	91
5	Benzamide, $\text{C}_6\text{H}_5\text{CONH}_2$	92
	<u>Carboxylic acids</u>	
6	Glyoxylic acid	below 0
7	Malonic acid, $\text{HOOCCH}_2\text{COOH}$	below 0
8	Oxalic acid, HOCCOOH	48
9	Benzoic acid, $\text{C}_6\text{H}_5\text{COOH}$	95
	<u>Alcohols</u>	
10	Benzyl alcohol, $\text{C}_6\text{H}_5\text{CH}_2\text{OH}$	61
11	Phenol $\text{C}_6\text{H}_5\text{OH}$	-30
12	p - Methyl phenol	-10
13	o - Methyl phenol	-8
14	m - Methyl phenol	Below -35
15	p - Chloro phenol	Below -35
16	D-Fructose	5
17	Vanilin p-HO m $\text{OCH}_3\text{C}_6\text{H}_3\text{CHO}$	42
18	p - Amino phenol	93
	<u>Amines</u>	
19	Aniline	44
20	Hydroxylamine hydrochloride	81

In order to demonstrate that the formation of the liquid ionic compound is the result of hydrogen bonding between Compound II and the chloride anion, attempts were made to prepare similar materials using various other starting materials, using the same procedure as Example 1. The results are shown in Table 2, as Comparative Examples 1 to 8.

In the same manner as described in Example 1, compounds were prepared from choline chloride (0.01 moles) and each of the compounds shown in Table 1A (0.02 moles). The freezing point of the resulting compound is shown in Table 1A

By contrast, the substances indicated in Table 2A, when substituted in the same molar quantity for the urea of Example 1 did not give an ionic liquid with a freezing point of 100°C or less.

<u>Table 2</u>		
<u>Comp Ex. No</u>	<u>Compound II</u>	<u>Fr Pt. of Melt (°C)</u>
	Amides	
1	Dimethylurea, $\text{NHCH}_3\text{CONHCH}_3$	149
	Esters and Ethers	
2	Anisole $\text{C}_6\text{H}_5\text{OCH}_3$	no melt formed.
3	4-Iodoanisole	no melt formed.
4	Diethyloxalate $(\text{C}_2\text{H}_5\text{OOC})_2$	no melt formed.
5	Diethylmalonate	no melt formed.
	Aldehydes and Ketones	
6	Benzyl methyl ketone	no melt formed
	Other	
7	Hexachloroethane	no melt formed.
8	Cyclohexane	no melt formed

Table 1A	
<u>Compound II</u>	<u>Fr Pt. of Melt (°C)</u>
<u>Amides</u>	
Allyl urea	9
Urea/H ₂ O ₂ complex	19
<u>Carboxylic acids</u>	
Trifluoroacetic acid	Below -40
Trichloroacetic acid	-24
Citric acid	26
Mandelic acid	33
Valeric acid	22
Tartaric acid	74
Phenyl acetic acid	-5
m-nitrobenzoic acid	85
p-hydroxybenzoic acid	97
Glutamic acid	13
m-aminobenzoic acid	39
<u>Alcohols</u>	
Ethanol	-20
Triethanolamine	-24
2-chloroethanol	6
Vanillin	17
p-hydroxybenzaldehyde	29
<u>Sugars</u>	
D(-) Fructose	5
D-glucose	14
<u>Amines</u>	
Diaminoethane	29
1,2-diaminopropane	63
<u>Misc.</u>	
Water	11
p-toluenesulphonic acid monohydrate	27
Dibenzenesulfonamide	39

Table 2A	
<u>Compound II</u>	<u>Fr Pt. of Melt (°C)</u>
<u>Carboxylic acids</u>	
salicylic acid	103
trans-cinnamic acid	101
3,5-dinitrobenzoic acid	104
nicotinic acid	126
stearic acid	no melt formed
hippuric acid	no melt formed
oleic acid	no melt formed
terephthalic acid	no melt formed
<u>Alcohols</u>	
9 - Anthracenemethanol	no melt formed.
Ethanol	no melt formed.
Propan-2-ol	no melt formed.
Mannitol	108
8-hydroxyquinoline	no melt formed
2-methyl salicylate	no melt formed
2-phenyl salicylate	no melt formed
<u>Sugars</u>	
Lactose	no melt formed
Saccharin	no melt formed
<u>Amines</u>	
Pyridine	no melt formed.
Benzyl amine	no melt formed.
triethylamine	no melt formed
<u>Esters and ethers</u>	
Ethyl cinnamate	no melt formed
<u>Aldehydes and ketones</u>	
Benzaldehyde	no melt formed.
<u>Amino acids</u>	
Glycine	no melt formed.
Alanine	no melt formed.
Lysine	no melt formed
Phenylalanine	no melt formed

Misc.	
Ferrocene	no melt formed.
Sarcosine	No melt formed.
Tetrabutylammonium hydrogen sulphate	159
1,2-dichloroethane	No melt formed.
Uric acid	No melt formed
Nitroethane	No melt formed.
Glycerol triacetate	No melt formed

The results in Tables 1, 2, 1A and 2A demonstrate that many but not all compounds which are in principle capable of donating a hydrogen atom to a hydrogen bond are capable of forming ionic liquids with choline chloride, by the method of Example 1. In general, the compounds which are form the most useful ionic compounds (i.e., those with the lowest freezing points) are ones in which the "Compound II" employed has a relatively low freezing point, for example, less than 150 °C, preferably less than 100°C, more preferably less than 50°C, and yet more which have a freezing point of 20°C, or less (i.e., which are solid at ambient temperature).

10

An additional factor which has an important bearing upon whether a particular hydrogen bond donor compound (II) is capable of forming an ionic liquid having a freezing point of 100°C or less is the difference between the degree of structure of the compound in the solid and liquid states. Compounds capable in principle of forming a hydrogen bond, but in which difference between the degree of structure in the solid and liquid states is low are generally not preferred. For example long chain aliphatic acids which have a low freezing point but a low degree of structure in the solid state are generally unsatisfactory. Likewise, compounds which are highly ordered in the liquid state (such as trifluoroacetic acid) are generally favoured.

20

Yet a further factor with important bearing upon whether a particular hydrogen bond donor compound (II) is capable of forming an ionic liquid having a freezing point of 100°C or less is the presence of different types of functional groups capable of acting as hydrogen bond donors. It is strongly preferred that only one type of functional group capable of acting as hydrogen bond donor is present in the compounds II. For Example, although two carboxylic acid groups may be present, compounds containing both a COOH group and an NH₂ group, (amino acids) are generally not preferred.

25

One of skill in the art will generally be capable of selecting a suitable hydrogen bond donor for the purposes of the invention, based on the foregoing criteria, and the specific Examples herein.

5

Example 16

The effect of changing the nature of the anion X^- was investigated, by repeating the procedure of Example 1, using choline nitrate, and choline tetrafluoroborate (0.01 mol) instead of choline chloride, in the procedure of Example 1. The freezing points of the

10 resulting compounds are shown in Table 3.

Table 3

<u>Example No</u>	<u>X⁻</u>	<u>Fr Pt. / °C</u>
21	BF ₄	67
22	NO ₃	4

Examples 23 to 41

15 The effect was investigated of substituting various other amine salts of Formula I, for the choline chloride of Example 1. In each case, 0.01 mol of the amine salt, as shown in Table 4, was heated with 0.02 mol of urea, until a clear melt was formed. Freezing points were measured by cooling, as before. The freezing points are shown in Table 4.

Table 4

20

<u>Ex.</u>	<u>R¹</u>	<u>R²</u>	<u>R³</u>	<u>R⁴</u>	<u>X⁻</u>	<u>Fr. Pt./°C</u>
1	Me	Me	Me	C ₂ H ₄ OH	Cl	12
23	Me	Me	Benzyl	C ₂ H ₄ OH	Cl	-33
24	Me	Me	Et	C ₂ H ₄ OH	Cl	-38
25	Me	Me	Me	Benzyl	Cl	26
26	Me	Me	Me	C ₂ H ₄ OCOMe	Cl	-14
27	Me	Me	Me	C ₂ H ₄ Cl	Cl	15
28	Me	Me	Me	ClCH ₂ CHOHCH ₂ (R)	Cl	65
29	Me	Me	Me	ClCH ₂ CHOHCH ₂ (S)	Cl	83
30	Me	H	H	H	Cl	33
31	Me	Me	H	H	Cl	29
32	Et	Et	Et	H	Cl	95
33	Et	Et	Et	Benzyl	Cl	36
34	Me	Benzyl	C ₂ H ₄ OH	C ₂ H ₄ OH	Cl	-6
35	Me	H	H	CH ₂ COOH	Cl	-3

36	Me	Me	Me	BrC ₂ H ₄	Br	84
37	Me	Me	Me	C ₂ H ₄ F	Br	55
38	Me	Me	Me	Me(CH ₂) ₁₁	Br	92
39	Et	Et	Et	Me	Br	9
40	Et	Et	Et	Benzyl	BF ₄	59
41	Me	Me	C ₂ H ₄ OH	C ₂ H ₄ OH	I	46

Comparative Examples 9 to 15

In the same way, salts of a symmetrical amine, as well as other amines of relatively high molecular weight were investigated, the results are shown in Table 5, as

- 5 comparative examples 9 to 12. These results demonstrate that unsymmetrical amine salts (R₁R₂R₃R₄ are not all identical) of relatively low molecular weight, are preferred.

Table 5

Comp		R1	R2	R3	R4	X-	F Pt./°C
9	Bu ₄ N	Bu	Bu	Bu	Bu	Cl	112
10	Me(CH ₂) ₁₃ (Me) ₃ N	Me	Me	Me	Me(CH ₂) ₁₃	Br	no melt formed
11	Me(CH ₂) ₁₇ (Me) ₃ N	Me	Me	Me	Me(CH ₂) ₁₇	Br	no melt formed
12	Hex(Et) ₃ N	Et	Et	Et	n-hexyl	Br	108

10

Examples 42 to 44

- 15 The effect of varying the anion X⁻ was investigated, using tetraethylammonium salts of various anions, in combination with urea, in the method of Example 1. The results are shown in Table 6.

Table 6

Example	Compound I cation	X ⁻	F Pt./°C
42	(Et) ₄ N	ClO ₄	99
43	(Et) ₄ N	O ₃ SCF ₃	59
44	(Et) ₄ N	CN	72
Comp.25	(Et) ₄ N	BF ₄	130
Comp 26	(Et) ₄ N	MeC ₆ H ₄ SO ₃	107
Comp 27	(Et) ₄ N	Br	113

Comparison of Example 21 with Comparative Example 25 illustrates broadly that asymmetrical amines are preferred.

Miscibility Tests


- 5 The miscibility of the material prepared in Example 1 with a number of common solvents was investigated. It was found to be miscible with methanol, DMSO, and water, and to form two layers with acetone, acetonitrile, acetophenone, bromobenzene, dichloroethane, diethylether, ethylacetate, hexane, propylene carbonate, and toluene. With THF, a white precipitate was formed.

10

Example 45

Use of Ionic Liquids as Battery Electrolytes

- Low freezing point ionic liquids prepared from compound II and amine salts can be used as electrolytes in batteries. Two such examples are described below. In the first, 7ml of the material of Example 1 (2:1 urea-choline chloride) was prepared and poured into separated compartments of a small glass cell. The compartments were separated by glass frit and each contained 3.5ml of ionic liquid. The cell was suspended in an oil bath so that the liquid temperature was maintained at 45°C. In one compartment 0.06g of FeCl₃ was dissolved and a carbon electrode inserted. A zinc electrode was immersed in the liquid contained in the other compartment. An Ecochemie PGstat 10 potentiostat was used to measure the potential difference between the electrodes – the maximum recorded value was 1.45V. The half cell reactions for this battery are;



- In the second example 7ml of 2:1 urea-choline chloride was prepared and divided between the two compartments of a glass cell as before. To one compartment 0.05 ml of Br₂ was added and a carbon electrode was inserted. A zinc electrode was immersed

30

in the liquid contained in the other compartment. The maximum value was 2.14V at 22°C. The half reactions for this battery are;



5 and,



Example 46 - Dissolution of metal oxides

10 An ionic liquid was prepared by heating two molar equivalents of urea with one molar equivalent of choline chloride in a suitable reaction vessel at approximately 70°C. Ruthenium oxide, copper (II) oxide, chromium (VI) oxide, vanadium pentoxide, lead (IV) oxide, manganese (IV) oxide and zinc oxide were all found to be soluble in the ionic liquid, in the temperature range 60°C to 120°C. None of the oxides of iron or
15 aluminium have shown significant solubility in the ionic liquids and hence these ionic liquids can be used to preferentially extract metal oxides from their ores. The metals can be extracted from the ionic liquids using electrowinning.

The 2:1 urea-choline chloride ionic liquid can also be used to process complex mixtures of metal oxides and allow electrowinning to be used to recover the metals.

20 This property of the ionic liquid and its relatively low bulk cost gives it the potential to be used to treat arc furnace dust on an industrial scale. Electric arc furnace dust containing iron (III) oxide (> 30%), zinc oxide (> 30%), aluminium oxide (~ 10%), silica (~ 5%), calcium oxide (~ 5%) and lead compounds (~ 5%) was used in this experiment. Normally it is treated as a waste product and buried in land fill sites.

25 However this is an expensive process and the lead content causes complications due to its high toxicity.

Zinc oxide and lead compounds can be dissolved in 2:1 urea-choline chloride and the respective metals subsequently electrodeposited onto a suitable cathode. Oxides of Fe,
30 Al, Si and Ca were found to be almost totally insoluble in the above ionic liquid. Urea-choline chloride ionic liquid was prepared by combining urea (0.02 moles) with choline chloride (0.01 moles) in a beaker and heating at 80 °C. Arc furnace dust (0.5g)

was added to the resulting clear colourless liquid and the mixture was heated at 80 °C for 1 hour. After 1 hour a brown suspension was obtained which was transferred to an electrochemical cell. Metal electrodeposition was achieved using a nickel cathode and a titanium anode (both electrodes were 50 mm by 10 mm and 1 mm thick) and
5 applying a potential difference of 3.5 V for 1 hour. Prior to electrodeposition the electrodes were gently abraded with glass paper and cleaned with acetone. After 1 hour of electrodeposition the nickel cathode was removed from the brown suspension, washed with acetone and dried. A thick charcoal coloured deposit was obtained. The electrodeposited material was analysed using Energy Dispersive Analysis by X-rays.
10 The results of the analysis revealed the presence of lead (77%), zinc (16%) and copper (7%). There was no trace of iron in the deposit thus showing that zinc oxide and iron (III) oxide can be separated and harmful lead compounds removed from arc furnace dust.

Dissolution of precious metal oxides

15

Other commercially important oxides for reprocessing include processes for the recovery of precious metals, in particular platinum and palladium, from materials in which they are present as oxides. Such mixtures occur, for example, in spent catalyst recovered from automobile catalytic converters. It would be highly desirable to be able
20 to recover such materials in a process which is economically viable. Generally the recovery of such metals from oxide mixtures involves dissolution of the oxide in strong acids, such as aqua regia.

25

We have discovered that the ionic liquids according to the invention, and in particular those where compound II is a carboxylic acid (preferably oxalic acid) are effective solvents for the dissolution of platinum and palladium oxides. The dissolved metals may be recovered from such solutions by electrowinning. For example, palladium oxide (in the form of spent catalyst supported on various substrates) can be dissolved in the 2:1 oxalic acid -choline chloride ionic liquid. In order to effect the dissolution,
30 the temperature is preferably maintained below 60°C. Palladium metal can subsequently be recovered by deposition onto a variety of substrates.

Example 47

An ionic liquid was formed by mixing oxalic acid (17.7g) and choline chloride (9.8g) at 60°C. To this a sample of automobile catalyst was added (3.16 g) which was
5 principally PdO on an alumina support. A grey suspension was initially formed which turned into a green solution when the Pd dissolved and the solid precipitated to the base of the cell. The solution was electrolysed using a Ni cathode and a titanium anode and an applied voltage of 5V for 30 min with an approximate current density of 1 mA cm⁻². At the end of this time a black deposit was obtained on the cathode. This was
10 analysed using energy dispersive analysis by x-rays and found to be primarily Pd metal.

Example 48 - Metal electrodeposition

The ionic liquids also find application in metal electrodeposition. Using, for example a
15 2:1 urea-choline chloride mixture copper, nickel, lead and zinc can be electrodeposited from their chloride salts and this finds application in reprocessing the said metals from industrial waste products.

Four portions of 2:1 urea-choline chloride mixture (0.2mol urea and 0.1mol choline
20 chloride) were prepared and heated at 80°C. The preparations were performed in sample tubes. A small quantity (0.001 mol) of a metal-containing compound (either CuSO₄.5H₂O, NiSO₄.6H₂O, PbCl₂ and ZnO) was added to one sample of ionic liquid and left to dissolve. Electrodeposition was then performed in each ionic liquid in turn using Pt electrodes 3mm in diameter polished with 1µm Al₂O₃ paste. In each
25 experiment a potential difference of 3V was applied for 10 min and the temperature was maintained at 80°C. For each of the metals, characteristic deposits were obtained on the negative Pt electrode.


2:1 urea-choline chloride ionic liquid (16 ml) was prepared by combining the reactants
30 in a beaker and heating at 80 °C. Cobalt (II) chloride hexahydrate (1.5 % wt) was added to the clear colourless ionic liquid and dissolved to give a blue liquid. The blue liquid was then poured into a PTFE electrochemical cell of internal dimensions 41 mm

long, 16 mm wide and 32 mm deep. A mild steel plate and a stainless steel plate, both 55 mm by 40 mm and 1 mm thick, were gently abraded with glass paper, cleaned with acetone and flame annealed. The steel plates were then placed parallel to each other along the inner lengths of the PTFE electrochemical cell. Cobalt deposition was achieved by connecting the mild steel and stainless steel plates to the negative and positive terminals respectively of a Thurlby Thander power pack. A potential was applied and adjusted so as to maintain a current density of 2 mAcm^{-2} for 30 minutes. An ISO-TECH IDM 66 Digital Voltmeter connected in series was used to monitor the current. The experiment was carried out at 60°C . After 30 minutes the mild steel plate was removed from the cell, rinsed with acetone and dried. With a current density of 2 mAcm^{-2} a semi-bright pale grey/brown homogenous deposit was obtained.

A separate portion of 2:1 urea-choline chloride ionic liquid (~5 ml) containing cobalt (II) chloride hexahydrate (1.5 % wt) was prepared and poured into an electrochemical cell at 60°C . Voltammetry was performed using a platinum microelectrode ($10 \mu\text{m}$ diameter), a platinum counter electrode and a cobalt reference electrode. An Autolab PGSTAT12 Potentiostat controlled by GPES software was used to carry out the cyclic voltammetry.

20 Reactions in Ionic Liquids

Heck reaction




The reaction between styrene and 4-iodo anisole in the presence of Pd(OAc)_2 and NaOAc at 130°C for 2 days gave 4-Iodoanisole with a 60% conversion to the product. Using 4-Bromoanisole gave 50% conversion to the product after 2 days under the same reaction conditions. 4-Chloroanisole did not react with styrene under similar conditions.


Using PdCl₂ as the catalyst the reaction is faster giving a 90% yield of the same product in 1.5 days.

When Na₂CO₃ is used as the base instead of NaOAc with PdCl₂ as the catalyst, the reaction time decreased and yield improved with 4-iodoanisole giving product with 96% yield in 16h. After removal of the product by distillation, the same melt and PdCl₂ catalyst (with the addition of more Na₂CO₃) was reused for the same reaction, giving product in 90% yield.

10 Polymerisation reactions in ionic liquids



This reaction yielded a polymer with a number average molecular weight of 12,000 with a polydispersity index of 3.2



15

This reaction yielded a polymer with a number average molecular weight of 12,800 with a polydispersity index of 3.2

Stainless steel electropolishing using 2:1 urea-choline chloride ionic liquid

20 Urea and choline chloride in a molar ratio of 2:1 (160 ml in total) were combined in a beaker and heated at 80 °C until a clear colourless liquid was obtained. The ionic liquid was then poured into a cylindrical electrochemical cell (internal diameter of 80 mm) suspended in an oil bath at 60°C. A zinc sheet was gently abraded using glass paper, degreased with acetone, shaped into a cylinder with a diameter of about 78 mm

25 and slid into the electrochemical cell. The zinc electrode was then connected to the negative terminal of a Thurlby Thander power pack. A stainless steel collar, approximately 40 mm in diameter, was suspended in the centre of the 2:1 urea-choline

chloride ionic liquid with the aid of a lead connected to the positive terminal of the Thurlby Thander power pack. A potential difference of 12 V was applied for 6 minutes after which time the stainless steel collar was removed from the ionic liquid, rinsed with acetone and dried. The stainless steel collar was found to be bright and reflective all over its surface. The procedure was repeated using other stainless steel collars and stainless steel fasteners of similar dimension and each time bright reflective finishes were obtained.

Stainless steel electropolishing using 2:1 ethanediol-choline chloride

Ethanediol and choline chloride in a molar ratio of 2:1 (20 ml) were combined in a beaker and heated at 80 °C until a clear colourless liquid was obtained. The ionic liquid was then poured into an aluminium electrochemical cell (internal length of 60 mm, internal width of 10 mm and internal depth of 40 mm) suspended in an oil bath at 25 °C. The outer wall of the aluminium cell was connected to the negative terminal of a Thurlby Thander power pack. A stainless steel plate, 50 mm by 10 mm and 1 mm thick, was degreased and suspended in the centre of the aluminium cell with the aid of a lead connected to the positive terminal of the Thurlby Thander power pack. A potential difference was applied and adjusted so as to maintain a current density between 60 and 70 mAcm⁻² at the stainless steel plate for 6 minutes. After 6 minutes the stainless steel plate was removed from the 2:1 ethanediol-choline chloride ionic liquid, rinsed with acetone and dried. The stainless steel plate was found to be bright and reflective all over its surface. The 2:1 ethanediol-choline chloride ionic liquid can be modified by the addition of lithium chloride (5 % wt). The increased chloride content of the ionic liquid increases the conductivity and thus lowers the power consumption during electropolishing. Stainless steel polished in 2:1 ethanediol-choline chloride containing lithium chloride is also very bright and reflective.

- R^6 , R^7 , R^8 , R^{10} are each H, a C_1 - C_8 alkyl group, an aryl group, or a C_7 - C_{12} alkaryl group optionally substituted with from 0 to 6 groups selected from OH, SR^5 , Cl, Br, F, I, NH_2 , CN, NO_2 , $COOR^5$, COR^5 and OR^5 , wherein R^5 is H, a C_1 to C_{10} alkyl or cycloalkyl group
- 5 R^9 is a C_1 - C_8 alkyl group, C_1 - C_{12} an aryl group, or a C_7 - C_{12} alkaryl group optionally substituted with from 0 to 6 groups selected from OH, SR^5 , Cl, Br, F, I, NH_2 , CN, NO_2 , $COOR^5$, COR^5 and OR^5 , wherein R^5 is H, a C_1 to C_{10} alkyl or cycloalkyl group, or NHR^{11} , wherein R^{11} is H or a C_1 - C_6 alkyl group, and Z is O or S.
5. An ionic compound as claimed in Claim 4, wherein compound II is urea,
10 acetamide, thiourea, glyoxylic acid, malonic acid, oxalic acid dihydrate, trifluoroacetic acid, benzoic acid, benzyl alcohol, phenol p-methyl phenol, o-methyl phenol, m-methyl phenol, p-chloro phenol, D-fructose, or vanillin.
6. An ionic compound as claimed in Claim 4, wherein compound II is urea, aniline or a substituted aniline, a C_1 - C_6 aliphatic acid, a C_1 - C_6 hydroxyaliphatic acid, or a
15 dicarboxylic acid of the formula $HOOC(CH_2)_nCOOH$, wherein n is 0 or 1, acetamide, a phenol or a substituted phenol, an alkylene glycol, or citric acid.
7. An ionic compound as claimed in Claim 4, wherein compound II is urea, acetamide, oxalic acid dihydrate, phenol, ethylene glycol, or citric acid.
8. An ionic compound as claimed in Claim 1, wherein Compound II has freezing
20 point of less than $160^\circ C$.
9. An ionic compound as claimed in Claim 7, wherein Compound II has a freezing point of $20^\circ C$ or less.
10. An ionic compound as claimed in Claim 1, wherein Compound II contains only one type of functional group capable of acting as hydrogen bond donor.
- 25 11. An ionic compound as claimed in Claim 1, wherein the molar ratio of I to II is about 1:2.
12. An ionic compound as claimed in any one of the preceding Claims, wherein R^4 is a C_1 to C_{10} alkyl or a cycloalkyl group, substituted with at least one group selected


from OH, Cl, Br, F, I, NH₂, CN, NO₂, COOR⁵, COR⁵, CHO and OR⁵, wherein R⁵ is as defined in Claim 1.

13. An ionic compound as claimed in any one of the preceding claims, wherein each of R¹, R², R³, independently is a C₁ to C₅ alkyl or a cycloalkyl group, and R⁴ is hydroxyalkyl.
14. An ionic compound as claimed in Claim 9, wherein each of R¹, R², R³, is methyl, and R⁴ is hydroxyethyl.
15. An ionic compound as claimed in any one of the preceding claims, wherein X is chloride.
16. An ionic compound as claimed in any one of the preceding claims, wherein R¹, R², R³, and R⁴ have the following meaning

R ¹	R ²	R ³	R ⁴
Me	Me	Me	C ₂ H ₄ OH
Me	Me	Benz	C ₂ H ₄ OH
Me	Me	Et	C ₂ H ₄ OH
Me	Me	Me	Benz
Me	Me	Me	C ₂ H ₄ OCOMe
Me	Me	Me	C ₂ H ₄ Cl
Me	Me	Me	ClCH ₂ CHOHCH ₂ (R)
Me	Me	Me	ClCH ₂ CHOHCH ₂ (S)
Me	H	H	H
Me	Me	H	H
Et	Et	Et	H
Et	Et	Et	Benz
Me	Benz	C ₂ H ₄ OH	C ₂ H ₄ OH
Me	H	H	CH ₂ COOH
Me	Me	Me	Et
Me	Me	Me	C ₂ H ₄ F
Me	Me	Me	Me(CH ₂) ₁₁
Et	Et	Et	Me
Et	Et	Et	Benz
Me	Me	C ₂ H ₄ OH	C ₂ H ₄ OH

17. An ionic compound according to any one of the previous claims in which the amine cation is chiral.

18. A method of preparing an ionic compound, having a freezing point of up to 100°C, which method comprises reacting at least one amine salt of the formula



5

with at least one organic compound (II) which is capable of forming a hydrogen bond with X⁻,

wherein R¹, R², R³ and R⁴ are each independently:-

H,

10

optionally substituted C₁ to C₅ alkyl,

optionally substituted C₆ to C₁₀ cycloalkyl,

optionally substituted C₆ to C₁₂ aryl

optionally substituted C₇ to C₁₂ alkaryl, or wherein

R¹ and R² taken together represent a C₄ to C₁₀ optionally substituted alkylene

15

group, thereby forming with the N atom of formula I a 5 to 11-membered heterocyclic ring,

X⁻ is NO₃⁻, F, Cl⁻, Br⁻, I, BF₄⁻, ClO₄⁻, CN⁻, SO₃CF₃⁻, or COOCF₃⁻, and wherein the term "optionally substituted" means that the group in question may or may not be

substituted with at one or more groups selected from OH, SH, SR⁵, Cl, Br, F, I,

20

NH₂, CN, NO₂, COOR⁵, CHO, COR⁵ and OR⁵, wherein R⁵ is a C₁ to C₁₀ alkyl or cycloalkyl group, wherein the molar ratio of I to II is from 1:1.5 to 1:2.5.

19. A method as claimed in Claim 18, wherein the reaction is carried out by heating the compound of formula I with the compound of formula II

25


20. The use of an ionic compound according to any of claims 1 to 17 as a solvent, as an electrolyte or as a catalyst.

21. A method of recovering a metal from a metal oxide, which method comprises forming a solution of the metal oxide in an ionic liquid as claimed in any one of claims 1 to 17, and electrolysing the solution to recover the metal.

22. A method as claimed in Claim 17, wherein the metal is platinum or palladium.

23. A method of electropolishing a metal article, which method comprises immersing the metal article in an ionic liquid as claimed in any one of claims 1 to 17, and applying a voltage to the article to electropolish the metal.

24. A method of forming a solution of a solute, which method comprises dissolving the solute in an ionic compound, having a freezing point of up to 100°C formed by the reaction of at least one amine salt of the formula



10 with at least one organic compound (II) which is capable of forming a hydrogen bond with X⁻,

wherein R¹, R², R³ and R⁴ are each independently:-

H,

optionally substituted C₁ to C₅ alkyl,

15 optionally substituted C₆ to C₁₀ cycloalkyl,

optionally substituted C₆ to C₁₂ aryl

optionally substituted C₇ to C₁₂ alkaryl, or wherein

R¹ and R² taken together represent a C₄ to C₁₀ optionally substituted alkylene group, thereby forming with the N atom of formula I a 5 to 11-membered

20 heterocyclic ring, X⁻ is NO₃⁻, F, Cl⁻, Br⁻, I, BF₄⁻, ClO₄⁻, CN⁻, SO₃CF₃⁻, or COOCF₃⁻,

and wherein the term "optionally substituted" means that the group in question may

or may not be substituted with at one or more groups selected from OH, SH, SR⁵,

Cl, Br, F, I, NH₂, CN, NO₂, COOR⁵, CHO, COR⁵ and OR⁵, wherein R⁵ is a

C₁ to C₁₀ alkyl or cycloalkyl group,

25 wherein the molar ratio of I to II is from 1:1.5 to 1:2.5.